

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

148 526
A1

12

EUROPEAN PATENT APPLICATION

21 Application number: 84201797.2

51 Int. Cl.: B 27 K 3/34, A 01 N 25/02

22 Date of filing: 04.12.84

30 Priority: 21.12.83 US 564121

71 Applicant: JANSSEN PHARMACEUTICA N.V.,
Turnhoutsebaan 30, B-2340 Beerse (BE)


43 Date of publication of application: 17.07.85
Bulletin 85/29

64 Designated Contracting States: AT BE CH DE FR GB IT
LI LU NL SE

72 Inventor: Van Dyck, Paul Constant Martin,
Gemeenschapslaan 1, B-2160 Brecht (BE)
Inventor: Ligtvoet, Theo Frans Maria Cornelius,
Antwerpsweg 169, B-2151 Vilmeren (BE)
Inventor: Van Leemput, Leo Jan Jozef, Sint
Hubertusdreef 18, B-3118 Wakkerzeel-Haacht (BE)

54 Water-dilutable wood-preserving liquids.

57 A water-dilutable wood-preserving liquid containing
from 10% w/w to 80% w/w of a suitable solvent, from 20%
w/w to 80% w/w of a suitable solubilizer and from 0.01%
w/w to 10% w/w of an azole of formula



or an acid-addition salt thereof.

EP 0 148 526 A1

0148526

JAB 439

5

10

WATER-DILUTABLE WOOD-PRESERVING LIQUIDS.

15

20 The present invention is concerned with organic wood-preserving liquids which are dilutable with predominantly aqueous mediums.

 Since it is desirable to preserve wood from decay caused by microorganisms several compounds having antimicrobial properties have been described as useful wood-preserving agents.

25 As wood is considered, for example, wood products such as timber, lumber, railway sleepers, telephone poles, fences, wood coverings, wicker-work, plywood, particle board, waferboards, clipboard, joinery, bridges or wood products which are generally used in housebuilding.

 Wood which is preserved from staining and decay is meant to be
30 protected from moulding, rotting, loss of their useful mechanical properties such as breaking strenght, resistance to shock and shearing strenght, or decrease of their optical or other useful properties such as the occurrence of odor, staining, spot formation and dote caused by the following microorganisms: Aspergillus species, Penicillium
35 species, Aureobasidium pullulans, Sclerophoma pityophilla,

Verticillium species, Alternaria species, Rhizopus species, Mucor species, Paecilomyces species, Saccharomyces species, Trichoderma viride, Chaetomium globosum, Stachybotrys atra, Myrothecium verrucaria, Oospora lactis and other staining and wood decay fungi.

- 5 Special emphasis should be led on the good activity against moulds and staining fungi such as Aspergillus niger, Penicillium funiculosum, Trichoderma viride, Alternaria alternata, decay and softrot fungi such as Chaetomium globosum, Trychophyton mentagrophytes, Coriolus versicolor, Coniophora cerebella, Poria monticola, Merulius (Serpula)
- 10 lacrymans and Lenzites trabea, and yeasts such as Candida albicans and Saccharomyces species.

In order to protect wood from decay it is treated with formulations containing one or more wood-preserving agents. Such treatment is applied by several different procedures such as, for

15 example, by treating the wood in closed pressure- or vacuum systems, in thermal- or dip systems and the like, or by a wide variety of exterior wood-structure treatments, e.g. by brushing, dipping, spraying or soaking the wood with the formulation containing the wood-preserving agent.

- 20 Whereas anorganic compounds were used as wood-preserving agents the more recently preferred agents are organic compounds, such as, for example, the azoles described in European Patent No. 38,109. Due to their organic nature these compounds have rather lipophilic properties, resulting in a good solubility in organic mediums and an
- 25 often inadequate solubility in aqueous mediums. Consequently these organic agents are usually incorporated in organic formulations for applying them to the wood.

However, these organic formulations have some less advantageous properties such as, for example, their expense combined with

30 disadvantageous influences on the environment and the safety and health of the applicator. Therefore a number of organic liquids which form emulsions or dispersions with aqueous mediums have recently been developed, such as the organic liquids described in U.S. Patent No. 4,357,163. However these emulsions or dispersions, formed

35 after mixing the organic liquid with the aqueous medium, are known to

be too liable to a number of factors, such as, for example, changes of temperature, pH of the mixture and/or hardness of the water used, the presence of impurities in the wood and the like, resulting in an often inadequate physical stability.

- 5 Additionally, because a rather invariable concentration of the active agent in the formulation is required to assure a continuous process in closed pressure- or vacuum systems or in thermal- or dip techniques, lack of uniform uptake of the suspension or dispersion by the wood negatively influences the applicability of said suspensions
10 or dispersions in such techniques. Such lack of uniform uptake causes a decreasing or increasing concentration of the active agent in the remaining formulation, which may finally result in a dilution of the formulation respectively a precipitation of the wood-preserving agent.

The present invention is concerned with organic wood-preserving
15 liquids which are dilutable with predominantly aqueous mediums, said liquids containing:

- 1) from 10% to 80% of a suitable solvent;
- ii) from 20% to 80% of a suitable solubilizer; and
- 20 iii) from 0.01% to 10% of at least one azole having the formula



or an acid addition salt thereof, wherein X is nitrogen or a CH group
25 and R_1 is a radical of the formula



wherein Z is a group $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}_2-\text{CH}_2-\text{CH}_2-$, $-\text{CH}(\text{CH}_3)-\text{CH}(\text{CH}_3)-$
30 or $-\text{CH}_2-\text{CH}(\text{alkyl})-$, wherein said alkyl is a straight or branched C_1-C_{10} alkyl radical; said Ar is a phenyl group which is optionally substituted with 1 to 3 halogens, C_1-C_6 alkyl radicals, C_1-C_6 alkoxy radicals, cyano-, trifluoromethyl- or nitro groups, a thienyl-, halothienyl-, naphthalenyl- or fluorenyl group; and, said R is C_1-C_{10}
35 alkyl, cycloalkyl, cycloalkyl lower alkyl, lower alkenyl, aryl lower

alkyl, aryloxylower alkyl or a radical of the formula $-O-R_o$, wherein said R_o is C_1-C_{10} alkyl, lower alkynyl or aryl-lower alkyl, wherein said aryl radical is phenyl, naphthalenyl or substituted phenyl, wherein said substituted phenyl has 1 to 3

5 substituents selected from the group consisting of halo, cyano, nitro, phenyl, lower alkyl and lower alkoxy, provided that when more than one substituent is present only one thereof may be cyano, nitro or phenyl.

The said wood-preserving liquids have the advantage that almost instantaneously homogeneous solutions are formed by mixing these
10 liquids with predominantly aqueous mediums. Furthermore, these solutions have an extremely high physical stability, not only at ambient temperature, i.e. at temperatures comprised between 15°C and 35°C, but also at decreased temperatures. Even after several cycles of crystallization of the aqueous solution below 0°C and subsequent
15 storage at ambient temperature the physical stability is not negatively influenced.

The homogeneous solutions combine also a good moistening of the wood-surface with a high degree of penetration of the said solutions in the wood, resulting in an unexpectedly high uptake of the solution
20 by the wood, and, consequently, a desired preservation of the treated wood.

Additionally, due to a uniform uptake of the aqueous solution the wood-preserving liquids and the resulting aqueous solutions are particularly useful in treatment techniques which require the
25 possibility of a continuous process, such as, for example, impregnation- or dip techniques.


Besides the previously cited advantages the subject compositions have also the advantage that the same protection of the treated wood is obtained at lower amounts of active ingredient taken up by the wood
30 when aqueous solutions are used than when solvent-based mixtures are used.

In addition the solutions formed with the wood-preserving liquids combine the hereinabove mentioned advantages with those which are characteristic to predominantly aqueous mediums, such as, for example,
35 a relatively high flashpoint, reduced toxicity resulting in

advantageous influences on the environment and the health and safety of the applicator, lack of irritation and the like.

Particularly interesting liquids in accordance with the present invention are those containing an agent of formula

5



wherein X has the above-identified meaning and R_1' is a radical of

10

the formula




wherein Z' is a group $-\text{CH}_2-\text{CH}_2-$, $-\text{CH}_2-\text{CH}_2-\text{CH}_2-$, $-\text{CH}(\text{CH}_3)-\text{CH}_2-$, $-\text{CH}(\text{C}_2\text{H}_5)-\text{CH}_2-$, $-\text{CH}(\text{C}_3\text{H}_7)-\text{CH}_2-$, $-\text{CH}(\text{CH}_3)-\text{CH}(\text{CH}_3)-$ or


15 $-\text{CH}(\text{CH}_3)-\text{CH}(\text{C}_2\text{H}_5)-$; Ar' is unsubstituted phenyl or phenyl substituted with 1 to 3 halogen atoms, preferably chloro atoms, C_1-C_6 alkyl radicals, C_1-C_6 alkoxy radicals, cyano or nitro groups; and R' is C_1-C_6 alkyl or C_3-C_4 alkenyloxy.

More particularly interesting liquids in accordance with the present invention are those containing an agent of formula

20



25 wherein X has the above-identified meaning and R_1'' is a radical of the formula



30

wherein R'' is C_1-C_4 alkyl, C_3-C_4 lower alkenyloxy, R_3 is hydrogen or C_1-C_3 alkyl and n is 1 or 2.

Preferred liquids in accordance with the present invention are those containing 1-[2-(2,4-dichlorophenyl)-1,3-dioxolan-2-ylmethyl]-

35 1H-1,2,4-triazole, generically designated as azaconazole, or a

suitable acid addition salt thereof.

As it is required that the wood-preserving liquid forms a homogeneous solution with a predominantly aqueous medium the solubilizer must sufficiently solubilize the active agent and the solvent of the liquid in the aqueous medium and may not negatively influence the solubility of the active agent in the solvent.

Preferred solubilizers are selected from the group consisting of:

- i) addition products of 1 to 60 moles of ethylene oxide with 1 mole of a phenol which is further substituted with at least one C_1-C_{15} alkyl group; and
- ii) addition products of 1 to 60 moles of ethylene oxide with 1 mole of ricinus oil.

The most preferred solubilizers are selected from the group consisting of:

- i) addition products of 1 to 60 moles of ethylene oxide with 1 mole of nonylphenol or octylphenol; and
- ii) addition products of 1 to 60 moles of ethylene oxide with 1 mole of ricinus oil.

The organic solvent of the liquid must fulfill the requirements of sufficiently solubilizing the active ingredient and, combined with the solubilizer, being homogeneously miscible with a predominantly aqueous medium.

Preferred solvents are 2-butoxyethanol and butyl 2-hydroxyacetic acid ester.

In the formulations of the present invention the azoles of formula (I) can also be used in combination with other compounds having a useful activity such as, biocidal compounds, e.g. antimicrobial agents, insecticides and the like.

As antimicrobial agents, which may be used in combination with the azoles of formula (I) there may be considered products of the following classes:

Phenol derivatives such as 3,5-dichlorophenol, 2,5-dichlorophenol, 3,5-dibromophenol, 2,5-dibromophenol, 2,5-(resp. 3,5)-dichloro-4-bromophenol, 3,4,5-trichlorophenol, chlorinated hydrodiphenylethers such as, for example, 2-hydroxy-3,2',4'-trichlorodiphenyl ether.

- ph nylphenol, 4-chloro-2-phenylphenol, 4-chloro-2-benzylphenol, dichlorophene, hexachlorophen; aldehydes such as formaldehyde, glutaraldehyde, salicylaldehyde; alcohols such as phenoxyethanol; antimicrobially active carboxylic acids and their derivatives;
- 5 organometallic compounds such as tributyltin compounds; iodine compounds such as iodophores, iodonium compounds; mono-, di- and polyamines such as dodecylamine or 1,10-di(n-heptyl)-1,10-diaminodecane; quaternary ammonium compounds such as benzyl-dimethyldodecylammonium chloride, dimethyldodecylammonium chloride, benzyl-di(2-
- 10 hydroxyethyl)dodecylammonium chloride; sulfonium- and phosphonium compounds; mercapto compounds as well as their alkali, earth alkaline and heavy metal salts such as 2-mercaptopyridine-N-oxide and its sodium and zinc salt, 3-mercaptopyridazin-2-oxide, 2-mercaptoquinoxaline-N-oxide, 2-mercaptoquinoxaline-di-N-oxide, as well as the
- 15 symmetrical disulfides of said mercapto compounds; ureas such as tribromo- or trichlorocarbanilide, dichloro-trifluoromethyldiphenylurea; tribromosalicylanilide; 2-bromo-2-nitro-1,3-dihydroxypropane; dichlorobenzoxazolon; chlorohexidine; isothia- and benzisothiazolone derivatives.
- 20 As insecticidal agents which may be used in combination with the azoles of formula (I) the following classes of products may be considered: insecticides having a natural origin, e.g., nicotine, rotenone, pyrethrum and the like; chloridinated hydrocarbons, e.g., lindane, chlordane, endosulfan and the like; organic phosphor
- 25 compounds, e.g., diazinon, parathion, dichlorvos, dimethoate and the like; carbamates, e.g., carbaryl, aldicarb, methiocarb, propoxur and the like; biological insecticides, e.g., products originating from *Bacillus thuringiensis*; synthetic pyrethroids, e.g., permethrin, allethrin, cypermethrin, halothrin and the like.
- 30 Furthermore, the formulations of the subject invention may also contain additives which may improve their applicability, the chemical and/or physical stability and the like properties of the said formulations. Examples of such additives are naturally occurring and synthetic resins, e.g. wood resin, alkyd resin, polyurethane resin and
- 35 the like, drying oils, e.g. linseed oils, castor oil, fish oil,

0148526

-8-

standoil and the like, siccatives, e.g. naphth noat s and the lik ,
stabilization products, .g. UV absorbers, anti-oxydants and the like,
pigments, waxes with high softening points and th like.

5

EXPERIMENTAL PART.

The following examples are intended to illustrate and not to limit
the scope of the present invention. Unless otherwise stated all parts
therein are by weight.

- 10 In the following examples Cemulson NP 8® is a Trade Mark of a
mixture of addition products of nonylphenols with ethylene oxide,
wherein an average of 8 mole of ethylene oxide has been reacted with 1
mole of nonylphenol and Soprophor B® is a Trade Mark of a mixture of
addition products of ricinus oil with ethylene oxide. Octylphenol 8.5
15 is a mixture of addition products of octylphenols with ethylene oxide,
wherein an average of 8.5 moles of ethylene oxide has been reacted
with 1 mole of octylphenol.

A. Preparation of organic concentrates:

20 Example I

formulation 1: 3.3% w/w of azaconazole
1.8% w/w of lindane
50% w/w of 2-butoxyethanol; and
Cemulsol NP 8® ad 100%.

25 preparation:

3.3 Parts of azaconazole and 1.8 parts of lindane were added
portionwise to 50 parts of 2-butoxyethanol at 50°C. After complete
solubilization the mixture was cooled to 25°C and 44.9 parts of
Cemulsol NP 8® were added.

30 Example II

Following the preparation-procedure described in Example I the
following formulations were prepared:

formulation 2: 5% w/w of azaconazole
50% w/w of 2-butoxyethanol; and
35 Cemulsol NP 8® ad 100%.

- formulation 3: 1.8% w/w of azaconazol
3% w/w f lindane
56% w/w of Soprophor B®; and
butyl 2-hydroxyacetic acid ester ad 100 ml.
- 5
formulation 4: 5.0% w/w of azaconazole
10% w/w of permethrin
20% w/w of butyl 2-hydroxyacetic acid ester; and
63.8% w/w of Soprophor B®;
- 10
formulation 5: 5.0% w/w of azaconazole
10% w/w of carbosulfan
20% w/w of butyl 2-hydroxyacetic acid ester and
63.8% w/w of Cemulsol NP 8®.
- 15
formulation 6: 5.0% w/w of azaconazole
56% w/w Soprophor B®;
butyl 2-hydroxyacetic acid ad 100ml.
- 20 formulation 7: 5.7% w/w of azaconazole
48.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
2% w/w of colophonium resin.
- 25 formulation 8: 5.7% w/w of azaconazole
48.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
2% w/w of petroleum resin.
- 30 formulation 9: 5.7% w/w of azaconazole
48.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
2% w/w of alkyd resin 50W.

- 5 formulation 10: 5.7% w/w of azaconazol
45.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
5.0% w/w of alkyd resin 50W.
- 10 formulation 11: 5.7% w/w of azaconazole
40.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
10.0% w/w of alkyd resin 50W.
- 15 formulation 12: 5.0% w/w of azaconazole
1.2% w/w of acetic acid;
40.0% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
8.8% w/w of alkyd resin 50W.
- 20 formulation 13: 5% w/w of etaconazole (1-[[2-(2,4-dichloro-
phenyl)-4-ethyl-1,3-dioxolan-2-yl]methyl]-1H-
1,2,4-triazole)
50% w/w of butoxyethanol; and
45% w/w of Cemulsol NP 8®.
- 25 formulation 14: 10% w/w of etaconazole
20% w/w of octylphenyl 8.5;
2% w/w of acetic acid;
10% w/w of Polysolvan O®; and
58% w/w of Cemulsol NP 8®.
- 30 formulation 15: 5% w/w of etaconazole
56% w/w of Soprophor B®; and
39% w/w of Polysolvan O®.
- 35 formulation 16: 5.0% w/w of propiconazole (1-[[2-(2,4-dichloro-
phenyl)-4-propyl-1,3-dioxolan-2-yl]methyl]-1H-
1,2,4-triazol)

40.7% w/w of butyl 2-hydroxyacetic acid ester;
44.3% w/w of Soprophor B®; and
10% w/w of alkyd resin 50W.

5 B. Physical stability of the formulations:

Example III

100 Parts of formulation 1 was stored during 24 hours at 20°C and, subsequently, during 24 hours at -7.5°C. The said storage-cycle was
10 repeated during 14 days.

Although some of the formulations crystallized during the storage period at -7.5°C the mixture always completely homogenized during storage at 20°C without the precipitation of any crystals.

Example IV

15 Following the procedure described in Example III the formulations 2 - 16 were also stored during 14 days at 20°C and at -7.5°C.

The mixtures completely homogenized during the storage-period at 20°C without the precipitation of any crystals.

Example V

20 Aqueous solutions prepared by diluting the formulations 1-16 with distilled water to a final concentration of 100 - 10.000ppm of the active ingredient were stored during 24 hours at 20°C and, subsequently, during 24 hours at -7.5°C. The storage-cycle was repeated during 14 days.

25 Although most of the aqueous solutions crystallized or became heterogeneous during the storage period at -7.5°C the solutions homogenized or were easy homogenizable during the storage period at 20°C.

30 C. Uptake by the wood.

Example VI

Wood

Beech wood blocks of 2 cm x 2 cm x 2 cm were stored until needed
35 in desiccators containing saturated solutions of sodium bichromate ,

assuring a relative humidity of 52% at room temperature.


Active ingredient formulations

The organic solvent type preservative contained 10 g of azaconazole per litre of a solution consisting of white spirit, plastifying
5 co-solvents and resins. The waterborne type preservatives were prepared as described hereinabove.

Radiolabelled active ingredient

Azaconazole, specifically ^{14}C -labelled at the 2-ethyl carbon,

10



showed a specific activity of 2.22 $\mu\text{Ci}/\text{mg}$. Stock solutions
15 containing 2.5 mg ^{14}C -azaconazole per 25 ml distilled water or 1.25 mg ^{14}C -azaconazole per 20 ml white spirit were prepared.

Treatment solutions

Since an equal treatment solution strength of 3 g azaconazole per litre was chosen to compare the respective preservative types, the
20 active ingredient formulations were diluted with the appropriate solvents. At the same time radiolabelled active ingredient was spiked in order to facilitate analytical procedures. The composition of the treatment solutions containing azaconazole is given in table 1. Blank treatment solutions were prepared from the blank formulations using
25 identical dilution ratios.

Table 1 : The composition of the treatment solutions, containing azaconazole as active ingredient, used for dip treatment and impregnation treatment of beech wood blocks. Initial active ingredient concentration of 3000 ppm. Room temperature.

5

	liquid	stock solution A	stock solution B	H ₂ O ad	White Spirit ad	Xylene ad
10	formulation 2	15 g	12.5 ml	-	250 ml	-
	formulation 6	15 g	12.5 ml	-	250 ml	-
	Oil based - I	75 ml	-	25 ml	-	250 ml
	Oil based - II	75 ml	-	25 ml	-	250 ml
	Oil based - III	75 ml	-	25 ml	-	250 ml

- 15 Stock solution A : 100 µg ¹⁴C-azaconazole/ml distilled water
 Stock solution B : 50 µg ¹⁴C-azaconazole/ml white spirit

formulation of the oil based - I and oil based - II liquids :

- 20 10 g azaconazole
 50 g colophonium resin
 50 g dibutyl phthalate
 100 ml Polysolvan O®
 white spirit ad 1000 ml.

formulation of the oil based - III liquid :

- 25 10 g azaconazole
 50 g dibutyl phthalate
 100 ml Polysolvan O®
 white spirit ad 1000 ml.

30 Methods

A. Dip treatment

- The humidity conditioned wood blocks were placed individually in pre-weighed and labelled 50-ml glass beakers, and their weight was recorded. Five blocks were dried at 120°C during 24 hours to assess the 52% relative humidity moisture content. Three cubes were provided
- 35

for each preservative type-time combination; for each preservative-time combination on cube for blank treatment was included. The blocks were removed from their beakers, while 15-ml portions of the selected treatment solution were added to each beaker. The initial weight of the treatment solution was recorded. The blocks were dipped in the solutions and retained completely immersed by imposing the tip of a Pasteur pipette, fixed into a rack-mounted clamp. Beakers containing organic solvent type preservative were covered with Parafilm to reduce evaporation losses. After the selected contact time intervals, i.e. after 1 hour, 4 hours or 24 hours, the blocks were removed from the solution and fixed in the clamps to leak out. After 15-30 minutes this step was considered to be complete. The final weight of the treatment solution was assessed. After air-drying for 2 hours the treated blocks were placed in pre-weighed and labelled beakers and transferred to the 52% RH desiccator for storage. The desiccator was vented periodically to remove volatilized solvents.

Sample analysis

Treatments solutions

The radioactivity level of the treatment solutions, before and after the dipping treatment, was assayed by liquid scintillation counting (LSC). Solution aliquots of 1 ml were perfectly miscible with 10 ml Insta-Gel II (Packard) scintillator cocktail. A Packard Tri-Carb 4530 microprocessor controlled liquid scintillation spectrometer automatically performing quench and luminescence corrections and converting cpm (counts per minute) into dpm (disintegrations per minute) was utilized.

Wood blocks

Five consecutive 2-mm zones were marked on the surface of the blocks in a direction parallel to the wood fibers. The blocks were clamped in a bench-vice and each 2-mm zone was removed by rasping. The shavings were collected on a plastic sheet fixed on the bench-vice.

Quadruplicate 50-mg aliquots per 2-mm section were weighed into combustor-cones (Packard) and combusted in a Packard 306B Sample

Oxidiz r. Th produced $^{14}\text{CO}_2$ was trapped in Carbo-Sorb-II (Packard) (7 ml) and radiocounted in P rmafluor V (Packard) (12 ml), with the equipment described above.

5 Calculations

The amount of active ingredient, transferred from the treatment solution to the wood was calculated, starting from the radioactivity mass balance

$$10 \quad W_1 \cdot v \cdot \text{dpm}_1 = W_f \cdot v \cdot \text{dpm}_f + \text{dpm}_t \quad (1)$$

where W_1 equals the initial treatment solution weight (g), W_f the treatment solution weight (g) after dipping, dpm_1 and dpm_f the radioactivity levels (dpm/ml) at these procedure steps, v the treatment solution specific volume (ml/g) and dpm_t the total amount of radioactivity transferred from the solution during the dipping. Using the relation between the radioactivity levels of the initial treatment solution, dpm_1 (dpm/ml) and its active ingredient concentration, C_1 ($\mu\text{g/ml}$), the total active ingredient transfer was obtained from

$$x = \text{dpm}_t \cdot C_1 \cdot \frac{1}{\text{dpm}_1} \quad (2)$$

25 On, expressing the load of active ingredient per unit weight of dry wood equivalent, W_b (g), and combining equations (1) and (2) :

$$X/W_b = (W_1 \cdot \text{dpm}_1 - W_f \cdot \text{dpm}_f) \cdot v \cdot C_1 \cdot \frac{1}{\text{dpm}_1} \cdot \frac{1}{W_b} \text{ (in } \mu\text{g/g)} \quad (3)$$

UNCLASSIFIED

0148526

Table 2 : Amount of azaconazole ($x \pm 1$ S.D.), expressed in mg per gram oven-dry wood equivalent, transferred to beech blocks during dipping for various time intervals in three different active ingredient formulations. These amounts were calculated from the mass balance of azaconazole in the treating solutions before and after the dipping. Number of replicates = 3. Initial concentration of the treatment solution : 3 g a.i./litre. Room temperature.

	t = 1 hour	t = 4 hours	t = 24 hours
Waterborne			
formulation 2	0.608 (\pm 0.008)	1.019 (\pm 0.039)	1.858 (\pm 0.297)
formulation 6	0.924 (\pm 0.162)	0.952 (\pm 0.119)	1.810 (\pm 0.376)
Organic solvent			
Oil based I	0.530 (\pm 0.085)	0.835 (\pm 0.012)	1.643 (\pm 0.018)
Oil based II	0.212 (\pm 0.042)	0.279 (\pm 0.069)	0.510 (\pm 0.076)

Table 3 : Amount of azaconazole a.i. formulation ($x \pm 1$ S.D.), expressed in ml per gram oven-dry wood equivalent, transferred to beech blocks during dipping for various time intervals in three different active ingredient formulations. Number of replicates = 3. Initial concentration of the treatment solution : 3 g a.i./litre. Room temperature.

	t = 1 hour	t = 4 hours	t = 24 hours
Waterborne			
formulation 2	0.164 (\pm 0.023)	0.280 (\pm 0.023)	0.588 (\pm 0.051)
formulation 6	0.207 (\pm 0.067)	0.278 (\pm 0.040)	0.471 (\pm 0.063)
Organic solvent			
Oil based I	0.110 (\pm 0.016)	0.157 (\pm 0.021)	0.229 (\pm 0.003)
Oil based II	0.102 (\pm 0.021)	0.130 (\pm 0.024)	0.232 (\pm 0.027)

Tabl 4 : Estimated concentration of azaconazole ($\bar{x} \pm 1$ S.D.), expressed in mg per ml impregnated solution, in the solution transferred to beech blocks during dipping for various time intervals in three different active ingredient formulations. Number of replicates = 3. Initial concentration of the treatment solution : 3 g a.i./litre. Room temperature.

	t = 1 hour	t = 4 hours	t = 24 hours
Waterborne			
formulation 2	3.737 (\pm 0.468)	3.755 (\pm 0.223)	3.145 (\pm 0.236)
formulation 6	4.654 (\pm 0.710)	3.463 (\pm 0.077)	3.944 (\pm 1.061)
Organic solvent			
Oil based I	4.826 (\pm 0.080)	5.389 (\pm 0.688)	7.161 (\pm 0.387)
Oil based II	2.089 (\pm 0.254)	2.118 (\pm 0.171)	2.189 (\pm 0.079)

Table 5 : Amount of azaconazole as a.i., detected at different penetration depths, in beech blocks dipped for 1 hour in three different active ingredient formulations. Cumulative concentration over the whole block. Initial concentration of the treatment solution : 3 g a.i./litre. Room temperature.

	penetration depth					whole block
	0-2 mm	2-4 mm	4-6 mm	6-8 mm	8-10 mm	
	a)	a)	a)	a)	a)	b)
formulation 2	1.687	0.313	0.307	0.302	0.249	0.608
Oil based I	1.384	0.338	0.197	0.190	0.191	0.572

a) concentration in mg of azaconazole as a.i. per gram wood at 52% relative humidity

b) concentration in mg of azaconazol as a.i. per gram oven-dry wood equivalent

B. Impregnation treatment

- 5 The dried wood specimens were grouped in 5 sets of 15 pine blocks and 5 sets of 15 beech blocks, one set for each formulation type. A selected group was collected in a beaker, covered with a weight for ballasting, and positioned in a vacuum desiccator. Pressure was reduced to 10^{-3} mm Hg by a Leybold-Heraeus S8A vacuum pump. After 10 15 minutes, 200 ml of the chosen treatment solution was drawn into the desiccator through a tube leading to the beaker. Excessive foaming was avoided. When the blocks were covered, the vacuum was released. The beaker was removed from the desiccator and left for two hours to complete the impregnation. Next, the blocks were lifted from the 15 treatment solution, allowed to drip for 1 minute and weighed (weight after treatment: W_t). The blocks were air-dried at room temperature, in a forced ventilation fume-hood for 4 hours. Five blocks were taken at random for analysis, whereas the remaining blocks were stored at 25° C in the dark for fixation: five blocks were stored for 2 weeks, 20 five blocks for 7 weeks. The outlined procedure was followed for each of the 10 wood-formulation type combinations.

Active ingredient determination

Wood specimen

- The concentration of active ingredient in the wood blocks, 25 immediately after treatment was determined by radioassay. The blocks were clamped in a bench-vice and a symmetrical half was removed by rasping. The raspings were collected on a plastic sheet, and homogenized thoroughly. Quadruplicate 50-mg aliquots were weighed into Combusto-Cones (Packard) and combusted in a Packard 306B Sample 30 Oxidiser. The produced $^{14}\text{CO}_2$ was trapped in Carbo-Sorb II (Packard) (7 ml) and radiocounted as described hereinbefore in Permafluor V (Packard) (12 ml).

- Alternatively, wood raspings were solvent extracted, using dichloromethane for oil based formulations-treated blocks and methanol 35 for water dilutable formulations-treated blocks, in a solvent: solids

ratio of 20:1 (v:w). Four consecutive extractions, spread over a 24-hour period, were performed. The extracts were combined, adjusted to a known volume and radioassayed as described hereinbefore, using Insta-Gel II (Packard) as scintillation cocktail, added directly to 1-ml aliquots of the methanol extracts or to the solvent evaporation residue of 1 ml-aliquots of the dichloromethane extracts.

The calculated concentration of azaconazole in the wood, L_w (g a.i./kg wood), was obtained as follows:

$$L_w = U \cdot C_o \cdot \frac{1}{d_o} \cdot \frac{1}{W_o} \quad (1)$$

where U is the treatment solution uptake (in g per test block), C_o the a.i. concentration in the treatment solution (in g per litre), d_o the density of this solution (in kg per litre) and W_o the weight of the test block (in g). Alternatively, the azaconazole load can be expressed on a volume basis (kg a.i./m³ wood):

$$L_v = U \cdot C_o \cdot \frac{1}{d_o} \cdot \frac{1}{V} \quad (2)$$

where V is the volume of the wood blocks (6 cm³).

The determined concentration of azaconazole in the wood, immediately after treatment, was obtained by measuring the radioactivity levels.

Table 6: The weight of the test blocks, the uptake of azaconazole formulation during impregnation, and the concentration of active ingredient (a.i.) - expressed in g per kg wood or in kg per m³ wood - calculated from uptake or determined by radioassay ($\bar{x} \pm 1$ S.D.). Determined azaconazole concentrations are subjected to Duncan's Multiple Range test.

Wood species	Formulation	Oven-dry weight of blocks W_0 (g)	Treatment solution uptake U (g/block)	Calculated azaconazole concentration		Determined azaconazole concentration	
				g a.i./kg	kg a.i./m ³	g a.i./kg	kg a.i./m ³
PINE	Oil based II	3.00(+0.14)	2.51(+0.18)	2.92(+0.29)	1.46(+0.10)	2.93(+0.23)	1.48(+0.14)
	Oil based III	3.03(+0.11)	2.54(+0.20)	2.98(+0.27)	1.50(+0.12)	2.97(+0.34)	1.49(+0.17)
	formulation 6	3.03(+0.12)	4.13(+0.20)	4.10(+0.24)	2.06(+0.10)	4.21(+0.17)	2.13(+0.08)
	formulation 9	3.04(+0.14)	4.13(+0.25)	4.09(+0.37)	2.06(+0.12)	4.23(+0.53)	2.19(+0.21)
	formulation 17	3.05(+0.12)	4.19(+0.23)	4.12(+0.26)	2.09(+0.12)	4.31(+0.30)	2.22(+0.13)
BEECH	Oil based II	3.43(+0.15)	1.84(+0.18)	1.87(+0.20)	1.07(+0.10)	1.84(+0.22)	B 1.04(+0.10)
	Oil based III	3.54(+0.16)	2.01(+0.21)	2.01(+0.23)	1.19(+0.12)	1.80(+0.25)	B 1.04(+0.12)
	formulation 6	3.42(+0.09)	3.43(+0.36)	3.01(+0.31)	1.71(+0.18)	3.10(+0.38)	A 1.76(+0.22)
	formulation 9	3.49(+0.10)	3.45(+0.56)	3.01(+0.52)	1.72(+0.28)	3.05(+0.62)	A 1.77(+0.32)
	formulation 17	3.49(+0.08)	3.50(+0.30)	3.00(+0.22)	1.75(+0.15)	3.21(+0.30)	A 1.85(+0.20)

04

0148526

-21-

D. Efficacy

Exempl VII

5 I. EXPERIMENTAL PROCEDURE

I.1. Materials

a) Test fungus:

10 Coriolus versicolor 863 A or Coniophora puteana was grown on malt agar at 25°C in Petri dishes, having a diameter of 120 mm. 20-day-old cultures were used in the test.

b) Test wood:

Wood blocks (5 x 2 x 0.6 cm.) (beech or pine) were used as test material.

15 c) Test solutions:

Test solutions were made by dissolving a desired amount of the concerned formulation in distilled water or xylene.

I.2. Methods

20 a) Treatment of wood blocks with preservatives

Test blocks were oven dried for 18 hours at 100-110°C, cooled in a desiccator and weighed (i.e. initial dry weight).

25 Test blocks were weighed down in a Petri dish bottom and placed in a vacuum desiccator. The pressure was reduced to 40 mbar by a water suction pump, the blocks were impregnated with the preservative solution or the blanco solution through a tube leading to the Petri dish.

30 When the blocks were well covered, vacuum was released, the Petri dish was removed from the desiccator and left for four hours in order to saturate and sterilize the blocks. Control blocks were treated in a similar sterile manner by impregnating the wood blocks with a blanco solution.

Blocks were tamponed with sterile filter paper and weighed under sterile conditions (i.e. weight after treatment).

35 The amount of preservative taken up by the blocks was calculated

(1. . pres rvative in wood).

b) Inoculati n of blocks

After drying for six days in a laminar air flow chamber the blocks were transferred to the inoculum Petri dishes and exposed to the attack of Coriolus versicolor or Coniophora puteana by placing two blocks, one treated with preservative and one control block, on a stainless steel frame in the Petri dish. Pairs of blocks were chosen in the same weight range.

c) Duration of test

The test blocks were exposed to fungal attack for 8 weeks at 25°C. Petri dishes were put together in a plastic bag to avoid desiccation.

d) Examination of test blocks after exposure to fungal attack

The blocks were freed from adhering mycelium, oven dried for 18 hours at 100-110°C, allowed to cool in a desiccator and weighed (i.e. final dry weight).

II. RESULTS

Table 7 illustrates the toxic thresholds for the aqueous solutions and the oil based mixtures. Toxic threshold as used herein is the amount of azole per m³ of wood preventing the wood from decay in such an amount that 3 percent weight loss is effected.

The percentage of weight loss is found following the formula

$$\frac{\text{initial dry weight} - \text{final dry weight}}{\text{initial dry weight}} \cdot 100$$

and the amount of test compound absorbed per m³ of wood is found following the formula

$$\frac{(\text{weight after treatment} - \text{initial dry weight})}{d_{\text{sol}}} \cdot \frac{C_{\text{sol}}}{d_{\text{sol}}},$$

5

wherein C_{sol} and d_{sol} have the meaning of the concentration of the preservative in the test solution, respectively the density of the test solution.

10

Since it is unrealistic to define the exact amount of azole/m³ of wood preventing the wood from decay in such an amount that exactly 3 percent weight loss is effected, Table 7 illustrates the range wherein the exact amount is embraced. The said range is limited by a lower amount, i.e. the highest tested amount where more than 3 percent weight loss is effected, and a higher amount, i.e. the lowest tested amount where less than 3 percent weight loss is effected.

15

Table 7: Toxic threshold.

20

25


30

	diluted with	<u>Coriola versicolor</u> kg azaconazole/m ³	<u>Coniophora puteana</u> kg azaconazole/m ³
formulation 2	water	0.031-0.057	0.537-0.823
formulation 6	water	0.033-0.061	0.547-0.742
oil-based I	xylene	0.069-0.143	0.940-1.222

35

CLAIMS

- 1 1. A water-dilutable wood-preserving liquid containing
 2 1) from 10% w/w to 80% w/w of a suitable solvent;
 3 ii) from 20% w/w to 80% w/w of a suitable solubilizer; and
 4 iii) from 0.01% w/w to 10% w/w of at least one azole having the formula




(I)

- 5 or an acid addition salt thereof, wherein X is nitrogen or a CH group
 6 and R_1 is a radical of the formula




- 7 wherein Z is a group $-CH_2-CH_2-$, $-CH_2-CH_2-CH_2-$,
 8 $-CH(CH_3)-CH(CH_3)-$ or $-CH_2-CH(alkyl)-$, wherein said alkyl is a
 9 straight or branched C_1-C_{10} alkyl radical; said Ar is a phenyl
 10 group which is optionally substituted with 1 to 3 halogens, C_1-C_6
 11 alkyl radicals, C_1-C_6 alkoxy radicals, cyano-, trifluoromethyl- or
 12 nitro groups, a thienyl-, halothienyl-, naphthalenyl- or fluorenyl
 13 group; and, said R is C_1-C_{10} alkyl, cycloalkyl, cycloalkyl lower
 14 alkyl, lower alkenyl, aryl lower alkyl, aryloxy lower alkyl or a radical
 15 of the formula $-O-R_0$, wherein said R_0 is C_1-C_{10} alkyl, lower
 16 alkenyl, lower alkynyl or aryl lower alkyl, wherein said aryl radical
 17 is phenyl, naphthalenyl or substituted phenyl, wherein said substi-
 18 tuted phenyl has 1 to 3 substituents selected from the group
 19 consisting of halo, cyano, nitro, phenyl, lower alkyl and lower
 20 alkoxy, provided that when more than one substituent is present only
 21 on thereof may be cyano, nitro or phenyl.

- 1 2. A liquid according to claim 1 wherein the azole is selected
 2 from the compounds having the formula:




- 3 wherein X is N or CH and R₁' is a radical of the formula




- 4 wherein Z' is a group -CH₂-CH₂-, -CH₂-CH₂-CH₂-,
 5 -CH(CH₃)-CH₂-, -CH(C₂H₅)-CH₂-, -CH(C₃H₇)-CH₂-,
 6 -CH(CH₃)-CH(CH₃)- or -CH(CH₃)-CH(C₂H₅)-; Ar' is
 7 unsubstituted phenyl or phenyl substituted with 1 to 3 halogen atoms,
 8 preferably chloro atoms, C₁-C₆ alkyl radicals, C₁-C₆ alkoxy
 9 radicals, cyano or nitro groups; and R' is C₁-C₆ alkyl or
 10 C₃-C₄ alkenyloxy.

- 1 3. A liquid according to claim 1 wherein the azole is selected
 2 from the compounds having the formula



- 3 wherein X is N or CH and R₁" is a radical of the formula



- 4 wherein R" is C₁-C₄ alkyl, C₃-C₄ lower alkenyloxy, R₃ is
 5 hydrogen or C₁-C₃ alkyl and n is 1 or 2.

- 1 4. A liquid according to claim 1 wherein the azole is
2 1-[2-(2,4-dichlorophenyl)-1,3-dioxolan-2-ylmethyl]-1H-1,2,4-triazole.
- 1 5. A liquid according to any of claims 1 to 4 wherein the
2 solubilizer is selected from the group consisting of:
 - 3 i) addition products of 1 to 60 moles of ethylene oxide with 1
4 mole of a phenol which is further substituted with at least
5 one C₁-C₁₅ alkyl group; and
 - 6 ii) addition products of 1 to 60 moles of ethylene oxide with 1
7 mole of ricinus oil.
- 1 6. A liquid according to any of claims 1 to 4 wherein the
2 solubilizer is selected from the group consisting of:
 - 3 i) addition products of 1 to 60 moles of ethylene oxide with 1
4 mole of nonylphenol or octylphenol; and
 - 5 ii) addition products of 1 to 60 moles of ethylene oxide with 1
6 mole of ricinus oil.
- 1 7. A liquid according to any of claims 1 to 6 wherein the
2 solvent is 2-butoxyethanol or butyl 2-hydroxyacetic acid ester.
- 1 8. A water-dilutable wood-preserving liquid containing:
 - 2 i) from 10% w/w to 80% w/w of 2-butoxyethanol;
 - 3 ii) from 0.01% w/w to 10% w/w of 1-[2-(2,4-dichlorophenyl)-
4 1,3-dioxolan-2-ylmethyl]-1H-1,2,4-triazole or an acid
5 addition salt thereof; and
 - 6 iii) a mixture of addition products of nonylphenols with
7 ethylene oxide wherein an average of 8 moles of ethylene oxide
8 has been reacted with 1 mole of nonylphenol, ad 100% w/w.
- 1 9. A water-dilutable wood-preserving liquid containing:
 - 2 i) from 10% w/w to 80% w/w of butyl 2-hydroxyacetic acid ester;
 - 3 ii) from 0.01% w/w to 10% w/w of 1-[2-(2,4-dichlorophenyl)-
4 1,3-dioxolan-2-ylmethyl]-1H-1,2,4-triazole or an acid
5 addition salt thereof; and
 - 6 iii) a mixture of addition products of ricinus oils with
7 ethylene oxide, ad 100% w/w.
- 1 10. An aqueous mixture prepared by diluting a water-dilutable
2 liquid according to any of claims 1 to 9, for use in the
3 preservation of wood.



European Patent
Office

EUROPEAN SEARCH REPORT

0148526

Application number

EP 84 20 1797

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
D, A	EP-A-0 038 109 (JANSSEN PHARMACEUTICA) * Page 6, line 34 - page 7, line 3; page 8, lines 19-30; page 11, lines 1-7; page 11, line 30 - page 12, line 40; page 13, lines 13-22; claims *	1-10	B 27 K 3/34 A 01 N 25/02
A	--- EP-A-0 050 738 (BASF) * Example 5; claims *	1-10	
A	--- EP-A-0 057 035 (SHELL) * Page 2, line 21 - page 4, line 13; page 6, lines 6-13; examples 2-20, 32-42, 72; claims 1,3,4,9-15 *	1,5-9	
A	--- GB-A-2 072 505 (DESOWAG-BAYER) * Examples; claims 1-5,10,16,17 *	1,5-8 10	TECHNICAL FIELDS SEARCHED (Int. Cl.4) B 27 K A 01 N
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 22-03-1985	Examiner FLETCHER A.S.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			